Multi-purpose materials with environment-friendly, lightweight and durability

Plastic corrugated board

SUNPLY®

Thick plastic corrugated board

SUMIPANEL®

Polypropylene expanded foamed board

SUMICELLER®

**Product Catalog** 

Lightweight, durable, hygienic materials for many purpose and application



The polypropylene plastic corrugated boards Sunply®, Sumipanel® and the polypropylene expanded foamed board Sumiceller® have features with lightweight and stiffness that combine recycling with reuse. Sumika Plastech Co.,Ltd. continue developing distinguished high performance products on the basis of its outstanding plastics resin engineering technology to meet the needs of the time

#### Hollow structured board

#### **SUNPLY®**

Sunply® has featured with hollow structure that enable many users to meet many requests . The single layer type have a wade range of thickness between 1.5 and 7 mm lineups. The multilayer type consist of two different materials in three layers, offering multiple functions with its characteristics. Sunply® is mainly used as a replacement for cardboard boxes and deviders for packaging applications. Thus, the raw materials are suited for processing of packaging or many applications . Also, all materials keep laws and regulations with environment-friendly. As the high performance products, we can offer the valuable products on the basis of multi-layered process. Besides, you can choose the laminated products and line shaped for transversal direction by heated pressured process.

#### **SUMIPANEL®**

Sumipanel® is a thick and parallel hollow structured board between 9 and 15 mm. It has basically the same appearance as Sunply® except that the liners on the surface and ribs (central pillars) are thicker and higher rigidity.

A standard type made solely of PP, and a higher rigidity type, strengthened is talc, are available.


Sumipanel® is suited for a replacement from wooden materials, such as plywood, paper materials and reinforced cardboards etc, for eliminating paper and wood debris.

#### **Grade Lineup**

- Page 4
- Standard/ HPConductive/ HD
- Page 5
- ●Environmental measure/ HG (Sunply® Bio-eco)
- ●Durable anti-static/ SF (Sunply® Clean)
- Multilayered conductive/SD

- Page 7
- Standard/WNHigh rigidity /WT

- Page 6
- ●Rule lined shape by heat press/ HK, HS (Sunply® Netsu-Kei)
  - ■Lamination with foamed soft sheet/ HF (Sunply® F)





# Polypropylene expanded foamed board

#### **SUMICELLER®**

Sumiceller $_{\oplus}$  is a low expandedfoamed polypropylene board with a expansion ratio up to 3 times. Sumiceller $_{\oplus}$  has featured with a smooth surface by a closed-cell structure. It does not absorb water inside of products and has excellent chemical resistance. Besides the standard type, the multilayered types is line-uped, which has featured with two different materials such as durable anti-static, anti-bacterial on both surface.

#### Other related products

### Adhesive tape

Acrylic adhesive tape

Out Ace® Out Cloth®



The tapes has line-uped with a wide range purpose from general to special applications such as industrial materials, housing and construction, agriculture-related, etc.

Please contact our Adhesive products Dept. about detail products information

#### **Specifications**



- Standard products/1.3 3 times(Expanded foam ratio)
- ●Floor protection/ Sumiceller® Hard
- ■Woody pattern color/ WL (Sumiceller® Wood-Like)


Page 9

- ●Durable anti-static/ ST
- Anti-bacterial type/ KT
- ●Soft foamed sheet lamination/ Sumiceller® Yawara





#### **Manufacturing Bases**





# Standard products/ HP

#### 〈 Features 〉

OHollow structure board made of polypropylene.

OBasically 11 colors are available.


(Depending on thickness and weights, color line-ups are changed) OThe characteristic lightweight can be used for a wide range of applications by processing or board.

All of grades has anti-static and weather resistant treatments.

\* These features are not durable.

OAs all of grades has corona treatment, it is suitable for using by printing and laminating process.

#### Structure



#### **Applications**

- Industrial packaging material (packing, dividers, pads)
- Protection and cushioning material for packaging
- Board behind showcases in store and supermarket
- Print signs (for construction sites, sign boards, etc.)
- Protection board for construction and housing site etc.

					Standar	d colors					Special colo	rs		Maximum	Maximum
Grade Thickness Unit weight (mm) Unit weight			Natural White Light	Light green	Light blue	Gray	Black	Dark blue	Yellow	Orange	Red	Beige	width size (mm)	length siz (mm)	
HP 15025	1.5	250	•	Nege die										1050	
HP 20030	2.0	300	•											1350	
HP 25030		300												1820	
HP 25070	2.5	700	•											1350	
HP 30040		400	•											1000	
HP 30050	3.0	500	•	•		•	•	•		•			•	1820	
HP 30090		900	•											1350	2400
HP 40060	4.0	600	•	•	•	0	•	•	•	•	•	•			
HP 40070	4.0	700	•	•	•	•	•	•	•	•	•		•	1	
HP 50080		800	•	•	•	•	•		•	•	•		•		
HP 50100	5.0	1000	•	•	•	•	•	•	•	•	•	•	•	1820	
HP 50120		1,200	0	•	0	•	•								
HP 60160	6.0	1,600	•	•											
HP 70170	7.0	1,700	•	•			THE RESIDEN	12.51							

# Conductive product/ HD


#### ⟨ Features ⟩

OProducts has features of hollow structure and conductive effect made by polypropylene and carbon. OStatic electricity discharges along with liner and rib.

Surface resistivity: 10<sup>6</sup> Ω/□or less (Volume resistivity:  $10^6 / \Omega \cdot \text{cm}$  or less) OHD reduces dust by conductive effect.

Grade	Thickness (mm)	Unit weight g/m²	Black	Maximum width size (mm)	Maximum length size (mm)	
HD 30050	3.0	500	•		2400	
HD 40060	4.0	600	•	1820		
HD 50090	5.0	900	•			

#### Structure



Static electricity discharges along each surfaces through ribs

#### **Applications**

- Dividers and pads for mainly electronic industries.
- Protection and cushioning material for electronic parts
- Partitions and dividers in areas where dust is not prohibited and limited.

# Environment-friendly products/ HG Sunply® Bio-eco


#### ⟨ Features ⟩

OHG uses special raw materials which is made of plant origin on only both surfaces.

○HG can reduce the emission of CO₂ by 6.2% compared with standard grade.

OMulti layered sheets for only both surfaces.

#### Structure



Fixed size 1350mm (Width) x 2000 mm (Length)

## **Durable anti-static** products/ SF Sunply® Clean


#### (Features)

ODurable anti-static resin is extruded on both surfaces by the multilayered process.

Available to choose 6 colors

The anti-static effect keeps long time with almost the same when using the first time. even after washing with water. Surface resistance rate: 10<sup>10</sup> - 10<sup>13</sup> Ω/□

#### Structure




Grade	Thickness (mm)	Unit weight g/m²	Natural	White	Light green	Light blue	Gray	Black	Maximum width size (mm)	Maximum length size (mm)
SF 30050	3.0	500	•	•	•	•	•	•		2400
SF 40070	4.0	700	•	•	•	•	•	•	1820	
SF 50080		800	•	•	•	•	•	•		
SF 50100	5.0	1,000	•	•	•	•	•	•		

#### The total CO<sub>2</sub> emissions from manufacturing, transportation, and processing generated by Sunply®. Sunply<sub>8</sub>HP 5.16 Sunply<sub>8</sub> 484 Bio-eco / HG 000 400 Unit: Kg (CO2)/ (resin)

Reference Material: Cited from the 6th Japan LCA Academic Presentation Summary (March 2011) and trial calculations made with our company's product conditions.

#### **Applications**

- Industrial packaging material for an environmental measure (containers, dividers)
- Partition board



(Based on our company's measurement values)


#### **Applications**

- Packaging material for foods and pharmaceuticals industries (containers, dividers, pads)
- Packaging material for valued products or parts (containers, dividers, pads)
- Partitions and dividers in the areas where dust and contamination is not allowed or limited.

	K		
		T	
D			

# Multilayer conductive products/ SI (Features)

OContains carbon black only in the both surfaces by the multilayered process. However, ribs in hollow sections are non-conductive. (Surface resistance rate: 106  $\Omega/\Box$  or less) OSuitable for using containers and partitions when conductivity is not required for all the layers.



electricity from surfaces to ribs.

Grade	Thickness (mm)	Unit weight g/m²	Black	Maximum width size (mm)	Maximum length size (mm)	
SD 30050	3.0	500	•	1820		
SD 40060	4.0	600	•		2400	
SD 50090	5.0	900	•			



# Heated rule products/ HK, HS Sunply® Netsu-Kei

#### (Features)

#### Structure

ORuled by heat process

Made by polypropylene resin that is the same as the standard products/ HP. OThe product has good cushioning characteristics due to its closing air in the hollow section with interval of 35 mm.

OSuitable for wrapping or cushioning pads of rolls, coils and corner as well as for protecting floors



#### **Applications**

- Protection boards for rolled parts (Mainly metal tubes etc.)
- Protection boards for floor and wall
   Protection boards for moving
- Cover board for reels or spools

HK=Rolled without	paper	spool	type
-------------------	-------	-------	------

			Ro	lled produc	ots	Board products			
Grade	Thickness (mm)	Unit weight g/m²	Natural	Maximum width size (mm)	Fixed length size(mn)	Natural	Maximum width size	Fixed length size(mrl)	
HK 15025	1.5	250			50,000			2,400	
HK 30040	3.0	400		1310	25.000	•	1350		
HK 40060	4.0	600	•	1010	20,000		1000		
HK 50100	5.0	1,000	•		15,000				




#### HS=Rolled with paper spool type

			Ro	lled produ	cts	
Grade	Thickness (mm)	Unit weight g/m²	Natural	Maximum width size (mm)	Fixed length size(mm)	
HS 15025	1.5	250			50.000	
HS 30040	3.0	400		1100	25.000	
HS 40060	4.0	600		1100	25,000	
HS 50100	5.0	1.000			15.000	

# **Cushioned products by-laminated** with PE foam / HF Sunply® F

#### (Features )

OHF has a cushion performance by which is laminated with high ratio-foamed PE materials for only one side of the Sunply® HP. (Total thickness is 3.5 mm, thickness, included with the 1 mm thickness PE foam materials on the one side) Suitable for protection or cushion toward walls, floors, and furniture.





Grade	Thickness (mm)	Unit weight g/m²	Natural	Light blue	Fixed width size (mm)	Fixed length size (mm)	Packing unit
HF 25030	約3.5	300			910	1820	10

<sup>\*</sup> The density describes only base material weight.

# **Idvantages of Sumipanel®**



# 1.Lightweight!

The hollow structure makes it lighter than any woods board such as veneer, plywood, and paper, also available for reducing the weight of the products.

#### 2.Stiffness!

Products has stiffness for handling medium weight parts. Depending on application, you can choose appropriate grade from Products line. The WN grade is suitable for application with flexibility and impact resistance are required. The WT grade is suitable for stronger situation.

\* Please trial and check your usage before using the product.

#### 3.Clealiness!

The products is not corroded by , water. It also lessen the dust, such as paper mills and wood chips etc.. You can use more safety and clean condition by fulfilling by sealing on edges.

\* Please note that the condition under direct sunlight may the product and decrease the durability due to heat and ultraviolet.

# Standard product/ WN

#### 〈 Features 〉

OHollow thickness board made of polypropylene.

Available to choose two colors, white and gray.


Available to bend by heat process, enables a variety of application with this products.

OThe corona treatment, improves printability and lamination with other materials.



#### Structure

Core is a hollow structure by polypropylene-made board, same as the standard grade of Sunply®.



	Grade	Thickness (mm)	Unit weight g/m²	White	Gray	Maximum width size (mm)	Maximum length size (mm)
	WN 09180	9	1,800	•	•		
	WN 09200	9	2,000	•	•		
	WN 12250	10	2,500	•	•	1300	2400
)	WN 12450	12	4,500	•	•		
	WN 15330	15	3,300	•	•		

# Rigid type / WT

#### (Features)

OCombination of Talc and Polypropylene for rigidity performance.


OAvailable to choose two colors, natural and gray.

OAvailable for sealing edge process and bending by heat process as well as the standard type / WN.

OThe corona treatment, improves printability and lamination with other materials.


Grade	Thickness (mm)	Unit weight g/m²	Natural	Gray	Maximum width size (mm)	Fixed length size (mm)
WT 09300	9	3,000	•	•	1.300	
WT 12450	12	4,500	•	•	1,300	2,400
WT 15550	15	5,500	•	•	1,200	

# Structure



#### Application of Sumipanel®

- The side, bottom and lid panel in a medium or large sized container for medium weight parts.
- Lid board on the top and dividers on the pallet
- Pallets for production lines
- Shelf panel for showcases and storage cabinets
- Materials for spindle and pillow block toward scrolled products such as films or steel wires (side panel)
- •Core material for flip open doors of trucks
- Protection boards in cargo container
- Walls, dividers and side panels in cattle shed for pig or chicken (dividers)
- Signboards



# Standard products / Expanded foamed ratio 1.3 - 3.0 times

#### (Features )

OClosed-cell structure foamed board, made of polypropylene. OSmooth surface and flexibility compared to Sunplys.


OEasy to process such as cutting, printing, die, heat bending etc. Available to use hygienically by avoiding water, particle and dust inside of board as the products is not hollow structure like Sunply.

OSuitable to apply containers and boxes for food and pharmaceutical industries which have severe limitation for dusts and contaminations.

OEnhance printability and adhesion performance through the corona treatment

#### **Applications**

- Industrial packaging material (Container and box, dividers, pads)
- Protection board for packaging
- Protection board for transporting glass panels
- •Divider (pad) for an insulation material
- Signboard
- Core material for tatami
- Construction material
- Spacer Board for can, bin bottle etc. in packing.



Note) Anti-static treatment is not applied in the products (The level of the surface resistance rate is  $10^{17}\Omega/\Box$  or more)


Grade	Expanded foamed ratio	Thickness (mm)	Unit weight g/m²	Natural	Light blue	Standard width size (mm)	Standard length size (mm)
1310 070	1.3	1	700	•	•	1350	
3030 090		3	900	•	•		2000
3040 120	3.0	4	1.200	•	•	1250	2000
3050 150		5	1.500	•	•		

# Floor protection board/ Sumiceller® Hard

#### 〈 Features 〉

OClosed-cell structure foamed board made of polypropylene.

OOutstanding stiffness and bending performance compared to the standard Sumicellers. Suitable for floor protection. OSuitable to replace wood-based products. Lightweight and excellent in water and chemical resistance.





Note) Anti-static treatment is not applied in the products (The level of surface resistance rate is  $10^{17}\Omega/\Box$  or more)

Grade	Expanded foamed ratio	Thickness (mm)	Unit weight g/m²	Light blue	Standard width size (mm)	Standard length size (mm)	Packing unit
1430 19	3 1.4	3.0	1,930	•	900	1800	5

<sup>\*</sup> To be on sale by fixed sizes bases

# The Wood-grain type Sumiceller® (Wood-like) / WL


#### 〈 Features 〉

OClosed-cell structure foamed board made of polypropylene.

OWood-grain pattern Sumiceller®.

#### Structure

Single-layer foamed board



Closed-cell structure foar

Note) Anti-static treatment is not applied in the products
(The level of surface resistance rate is 10™0/□or more)

	Grade	Expanded foamed ratio	Thickness (mm)	Unit weight	Brownish black (black)	Reddish brown (brown)	Green	Antique white (white)	Standard width size (mm)	Standard length size (mm)
Ì	3030 090WL	3.0	3.0	900	•	•	•	•	1000	2000

<sup>\*</sup> To be on sale by fixed sizes bases

# **Durable anti-static products/ST**

#### (Features )

ODurable anti-static resin extrudes from both surfaces by the multilayered process .

OSuitable to apply containers and boxes for food and pharmaceutical industries which have severe limitation for dusts and contaminations.

Surface resistance rate: 10<sup>11</sup> - 10<sup>13</sup> Ω/□ or less



#### Structure

Layers on the both surface ( Durable anti-static effect )

Closed-cell structure foam

#### Applications

- •Industrial packaging material (Container and box, dividers,pads) •Packaging material mainly for food
- Packaging material mainly for food and pharmaceutical industries
- Packaging material for electronics and Liquid Crystal Display parts.

Grade	Expanded foamed ratio	Thickness (mm)	Uni tweight g/m²	Light blue		Standard width size (mm)	Standard length si ze (mm)
3030 090 ST		3	900	•			
3040 120 ST	3.0	4	1,200	•	•	1250	2000
3050 150 ST		5	1,500	•			

# Antibacterial type/ KT

## 〈 Features 〉

OMultilayered closed-cell structure foam board based on ST grade.

OKT also add the durable anti-static effect.

hickness (mm)	Unit weight g/m²	Light blue	Standard width size (mm)	Standard length size (mm)	Packing unit	
3	1,020	•	1250	2000	3	
4	1 200		1050	0000	2	

<sup>3040 132</sup> KT 3.0 4

\* To be on sale by fixed sizes bases

Grade 3030 102 KT Expanded foamed ratio

3.0



Refer to page 11 for the explanation of the mark

# Lamination with PE foam products / Yawara

#### (Features)


OSoft cushioned board with a higher shock-absorbing material (high-foam PE sheet) is laminated on the both sides of the standard grade. (Thickness of 3mm grade and . Thickness of PE foam material approximately 1 mm). OAnti-static treatment is treated with both surfaces for the white and pink colors products. For the Yawara Pink, a durable anti-static performance is provided to the polyethylene foam. For the Yawara White, the polyethylene film on the surface provides an anti-static performance.

OAvailable to use products without difference of direction. A smooth surface for any direction.

Gra	de	Total thickness (mm)	Uni tweight g/m²	White	Pink	Standard width size (mm)	Standard length size (mm)	Packing unit
Yawara-white	4230 064	4.5	640	•		1000	1500	10
Yawara-pink	4030 068	4.5	680		•	1000	1300	10

<sup>\*</sup> The density g/m² of the base material. \* To be on sale by fixed size bases

#### Structure





# Typical Mechanical and physical properties of Sunply®\*These properties are representative and not guaranteed.

									Standar	d grades			
	Item		SI unit	Measuring condition	HP15025	HP20030	HP25030	HP25070	HP30040	HP30050	HP30090	HP40060	HP40070
	Thickness		mm	Company's test method	1.5	2.0	2.5	2.5	3.0	3.0	3.0	4.0	4.0
	Unit weight		g/m <sup>2</sup>	Company's test method	250	300	300	700	400	500	900	600	700
	Apparent density	/	kg/m <sup>3</sup>	Company's test method	167	150	120	280	133	167	290	150	175
End	crash .	MD	N	50 mm	21.1	29.7	29.7	136.4	48.2	63.0	133.0	98.2	127.0
Eliu	Clasii	TD	N	interval	0.72	1.3	1.3	24.2	2.7	6.0	29.8	8.8	11.1
Flat	crash	-	MPa	50 mm angle	0.20	0.22	0.22	1.53	0.21	0.30	0.80	0.39	0.45
	M D	MD	N/cm	Based on	8.3	11.2	11.2	29.4	28.8	36.2	66.9	62.8	89.1
Bending	Elasticity	TD	N/cm	JIS-K7171	0.78	1.2	1.2	13.7	2.7	6.0	29.8	8.6	12.9
by 50 mm span		MD	N	Bending speed	2.9	3.9	3.9	10.8	7.3	9.6	20.4	15.7	22.4
Span	Strength	TD	N	10mm/min	0.33	0.46	0.46	5.3	1.4	2.5	9.6	3.6	6.0
		MD	N/cm	Based on	0.65	0.94	0.94	5.4	3.8	4.5	9.6	9.9	14.4
Bending	Elasticity	TD	N/cm	JIS-K7171	0.35	0.47	0.47	3.5	0.91	1.6	6.1	2.3	3.6
by 100 mm span	C	MD	N	test method Bending speed	1.0	1.4	1.4	5.7	2.9	3.9	9.1	7.1	10.2
	Strength	TD	N	10mm/min	0.18	0.23	0.23	3.5	0.50	1.0	7.0	2.0	3.1
		23°C	N•cm	JIS-K7211	1471	392	221	275	66	105	371	198	247
Du Pont/ Impact strength -10°C	-10°C	N•cm	Impact core 1/2inch φ	1471	186	50	251	24	46	253	84	109	

							Standard grades			Bio-eco
	Item		SI unit	Measuring condition	HP50080	HP50100	HP50120	HP60160	HP70170	HG50100
	Thickness		mm	Company's test method	5.0	5.0	5.0	6.0	7.0	5.0
	Unit weight		g/m <sup>2</sup>	Company's test method	800	1,000	1,200	1,600	1,700	1,000
/	Apparent density		kg/m <sup>3</sup>	Company's test method	160	200	240	267	243	200
End	crash	MD	N	50 mm	157.2	205.9	274.6	410.0	437.0	
End	.lasii	TD	N	interval	13,3	31.0	39.0	56.8	61.6	
Flat	rash	_	MPa	50 mm angle	0.49	0.68	0.86	1.11	1.14	0.63
	20.00 10000000	MD	N/cm	Based on	121.3	147.5	219.7	416.4	477.4	
Bending	Elasticity	TD	N/cm	JIS-K7171 test method	18.5	27.5	37.1	57.0	61.8	
by 50 mm span	2 7	MD	N	Bending speed	30.5	36.4	49.4	77.2	84.1	
	Strength	TD	N	10mm/min	9.2	12.4	16.8	26.3	28.6	
	et oraș	MD	N/cm	Based on	20.1	30.5	35.0	68.7	84.7	31
Bending	Elasticity	TD	N/cm	JIS-K7171	5.1	8.3	14.5	22.4	22.7	В
by 100 mm span	Channella	MD	N	test method Bending speed	13.8	19.5	26.5	41.5	45.3	21
	Strength	TD	N	10mm/min	4.6	8.7	11.9	18.9	20.7	8
		23°C	N•cm	JIS-K7211	293	364	389	296	370	
Du Pont/Imp	oact strength	-10°C	N•cm	Impact core 1/2inch φ	136	192	246	242	270	

						Persistent	anti-static			Conductive		Multilayer conductive		
	Item		SI unit	Measuring condition	SF30050	SF40070	SF50080	SF50100	HD30050	HD40060	HD50090	SD30050	SD40060	SD50090
	Thickness		mm	Company's test method	3.0	4.0	5.0	5.0	3.0	4.0	5.0	3.0	4.0	5.0
	Unit weight		g/m <sup>2</sup>	Company's test method	500	700	800	1,000	500	600	900	500	600	900
	Apparent density		kg/m <sup>3</sup>	Company's test method	167	175	160	200	167	150	180	167	150	180
End	crash	MD	N	50 mm	42.9	113.4	141.4	188.2	50.9	78.6	140.1	50.9	78.6	140.1
Liid	Clasii	TD	N	interval	1.1	9.1	12.3	17.6	4.70	7.4	13.4	4.7	7.4	13.4
Flat	crash	-	MPa	50 mm angle	0.16	0.30	0.37	0.51	0.69	0.49	0.7	0.53	0.27	0.14
		MD	N/cm	Based on	27.3	91.7	123.9	188.3	34.0	60.3	139.1	34.0	60.3	139.1
Bending	Elasticity	TD	N/cm	JIS-K7171 test method	2.2	7.9	10.7	16.4	5.31	7.2	12.7	5.3	7.2	12.7
by 50 mm span		MD	N	Bending speed	5.9	16.9	22.4	33.4	8.5	11.2	19.1	8.5	11.2	19.1
	Strength	TD	N	10mm/min	1.2	4.4	6.0	9.3	2.24	3.13	5.8	2.24	3.1	5.8
		MD	N/cm	Based on	4.3	14.2	19.2	29.1	5.40	9.82	23.1	5.40	9.8	23.1
Bending	Elasticity	TD	N/cm	JIS-K7171 test method	0.58	2.8	3.9	6.2	1.26	2.16	4.9	1.26	2.2	4.86
by 100 mm span	Carronally	MD	N	Bending speed	2.9	9.0	12.0	18.1	4.2	5.9	11.2	4.2	5.9	11.2
	Strength -	TD	N	10mm/min	0.35	2.8	4.0	6.4	0.90	1.68	4.0	0.90	1.7	4.02
		23℃	N•cm	JIS-K7211	90	121	136	166	132	199	349	408	488	666
Du Pont/Im	pact strength	-10°C.	N•cm	Impact core 1/2inch φ	33	46	52	65	48	104	231	177	227	336

### Electric properties of Sunply®

6 1	HP	SF	HD	SD	DK
Grade	Standard grades	Persistent anti-static	Conductive	Multi-layer conductive	Electrostatic diffusion
Added function	Contains (Low-molecular) surfactant.	Contains a high-polymer anti-static material only in the both surfaces.	Contains carbon black in all the layers.	Contains carbon black in the surface layer.	High-polymer anti-static material and carbon black
Surface resistance rate $(\Omega/\Box)$	10 11~13	10 10~13	10 <sup>6</sup> or less	10 <sup>6</sup> or less	108~10
Volume resistivity ( $\Omega \cdot cm$ )			10 <sup>6</sup> or less		107~9
Surface resistance between points (RP) ( $\Omega$ )	6				$1 \times 10^6 \sim 1 \times 10^7$ (RCJ standards)
Features	Depending on rinsing, etc. anti-static treatment will lose its function. (Untreated products 10 <sup>17</sup> - 10 <sup>20</sup> )	The anti-static function maintains long term.	Conductive properties are effect for all layers in products.	Conductive properties are effect only for both surfaces.	DK covers the middle range area between the conductive and the anti-static .

## Sunply<sub>®</sub> DK (Electrical diffusion properties products)

Sunply<sub>®</sub> DK is the advanced products with static electricity diffusion which has covered middle range area between the conductive and the anti-static. The static charge decay properties are compliant with the MIL and EIA standards (electronic packaging standards) Products is based on the regulation and the standard of static charge decay properties which are established by MIL and EIA.

#### Typical Mechanical and physical properties of Sumipanel®

\*These properties are representative and not guaranteed.

							Standard grades	1100			High rigidity	
	Item		Stunit	Measuring condition	WN09180	WN09200	WN12250	WN12450	WN15330	WT09300	WT12450	WT15550
	Thickness		mm	Company's test method	9.0	9.0	12	12	15	9.0	12	15
	Unit weight		g/m²	Company's test method	1800	2000	2500	4500	3300	3000	4500	5500
	pparent density kg/m³ Company's test method				200	222	208	375	220	333	375	367
End	crash	MD	N	50mm span	330	427	668	1723	1054	924	1671	2220
Liid	Clasii	TD	N	50mm 10mm/min	67	78	106	569	151	208	592	868
Flat	crash	-	MPa	50mmangle 10mm/min	1.69	1.65	1.55	7.25	1.39	3.79	4.54	5.21
		MD	N/cm	Based on JIS-K7171	98	154	273	584	422	335	1241	2000
0 1:	Elasticity	TD	N/cm	test method 50mmwidth	28	32	41	257	55	98	276	404
Bending		MD	N	8ending speed 10mm/min	58	72	105	237	158	91	241	366
	Strength	TD	N	Span interval 100mm	19	23	31	132	41	41	96	129
Du Pont/Impact strength		23°C	N∙cm	Based on JIS-K7211	489	713	1188	2346	1779	494	593	677
		N∙cm	test method impact core 1/2nch o	481	581	795	1283	1060	193	290	367	

#### Typical Mechanical and physical properties of Sumiceller

\*These properties are representative and not guaranteed .

				,, , , , , , , , , , , , , , , , , , , ,		Standar	d grades		Durable	anti-static prod	ucts (ST)	Hard	Yawara-white	Yawara-pink
	Item		SI unit	Measuring	1310 070	3030 090	3040 120	3050 150	3030ST	3040ST	3050ST	1430 193	4230 064	4030 068
	Thickness		mm	Company's test method	Company's test method 1.0 3.0 4.0 5.0 3.0 4.0 5.0		5.0	3.0	約4.5	約4.5				
	Unit weight		g/m²	Company's test method	750 700 900 1200 1500 900 1200 1500					1930	730	735		
	Apparent density		kg/m <sup>3</sup>	Company's test method	700 300 300 300 300 300 300					300	643	162	163	
		MD	N/cm		5.8	41.1	97.0	153.0	46.4	99.3	152.2	73.4	25.7	25.2
Bending in	Elasticity	TD	N/cm		4.5	22.5	72.9	123.3	23.4	57.0	90.7	64.8	13.3	13.7
S0 mm span		MD	N	Based on	4.0	13.4	24.2	35.0	15.0	24.3	33.6	20.2	11.6	11.8
	Strength	TD	N	JIS-K7171 test method	3.3	8.2	19.6	31.1	8.3	15.3	22.3	18.8	7.0	6.5
		MD	N/cm	Bending speed	0.5	4.7	12.8	20.9	5.3	13.1	20.8	11.0	3.6	4.5
Bending in	Elasticity	TD	N/cm	10mm/min	0.5	2.6	9.2	15.8	2.8	7.2	11.6	10.0	1.9	2.0
00 mm span	Strength	MD	N		1.0	5.4	10.6	15.8	6.1	10.7	15.2	12.6	4.3	5.3
	(yield point)	TD	N		1.0	3.1	8.1	13.2	3.2	6.3	9.5	11.9	2.2	2.4
		23°C		Base on JIS-K7211 test method	236	190	351	512	192	244	296	231	157	191
Du Pont/ Im	pact strength	-10°C	N·cm	Impact core	65	132	208	266	62	129	181	116	108	121

Note) Mechanical and physical properties of Sumiceller KT (antimicrobial) are the same as those of Sumiceller ST. Mechanical, and the physical properties of Sumiceller WL (Wood-Like) are also same as those of Sumiceller (standard type),

#### Antibacterial property of Sumiceller®KT

Test results of JISZ2801 (It supposed to be effective when the antimicrobial activity ratio is 2.0 or more)

●Comparison data between Sumiceller<sub>®</sub>ST (Non antibacterial products) and Sumiceller<sub>®</sub> KT


\*These properties are representative and not guaranteed.


Test specimen	Staphylocoo	cus aureus	Escherichia coli			
	Average viable bacteria count	Antibacterial activity value	Average viable bacteria count	Antibacterial activity value		
Sumicell er <sub>*</sub> ST	5.30		6.09			
Sumiceller•KT (Antibacterial type)	<-0.2	5.5	<-0.2	6.2		

●Sumiceller<sub>®</sub>KT is a registered products of the Society of Industrial Technology for Antimicrobial Articles (SIAA) certification.

The SIAA mark is a certification for an antimicrobial products that meet the three criteria of the antimicrobial property, safety, and appropriate labeling.

#### (Reference) Detail Test method of mechanical and physical properties





ISO22196 for KOHKIN 無機抗菌剂·辣込 両表面 JP012288A0001X

#### Please read the following precautions before using the product.

#### Handling precautions of Sunply<sub>®</sub>, Sumipanel<sub>®</sub>, and Sumiceller<sub>®</sub>

- Sunply®, Sumipanel®, and Sumiceller® are made of polypropylene (PP) resin
- Please refer to the separately prepared safety data sheets (SDSs) when using Sunply®, Sumipanel®, and Sumiceller®.
- The products have smooth and slippery surfaces. Ensure that the packing is securely packed. Watch your step carefully when walking or working on the product surface. Pay attention, especially when any fluid such as water or oil has adhered to the surface of the products. This may cause accidents.
- Please pay attention carefully with your hand or finger when handling the products.
- Please be careful not to cut your skin, when using a knife or the like to cut. the products.
- The physical performance of the products will become embrittlement when exposed to direct sunlight for a long time.
- Please use the products at room temperature.
- The products may have a risk of ignition when exposed to heat at approximately 400 °C. Please pay attention while handling the products in the vicinity of sparks or other fire sources. (The products are designated as flammables under the Japanese Fire Service Act.)
- In the case of an ignition, cut off from the fire sources and extinguish the fire with a fire-extinguishing agent. (Fire-extinguishing agents: fire foam, dry chemicals, carbon dioxide, plenty of water)
- Please do not drop or deliberately exert excessive impact on the products during loading and unloading to prevent them from bending, cracking, or chipping.
- Properly dispose of products in accordance with the laws concerning industrial waste management, or entrust the disposal to a waste disposal specialist.

End

#### Sumika Plastech Co., Ltd.

< Industrial Material Department >

Head Office : 3F, Kayabacho Takagi Bldg., 1-8 Nihonbashikoamicho, Chuo-ku, Tokyo103-0016